



## **Antioxidant and Anti Inflammatory Activity of Copper Nanoparticles Synthesized Using Red Tea**

**R. Bharathi <sup>a</sup>, Arvina Rajasekar <sup>b\*≡</sup> and S. Rajeshkumar <sup>c∞</sup>**

<sup>a</sup> *Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, India.*

<sup>b</sup> *Department of Periodontics, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, India.*

<sup>c</sup> *Department of Pharmacology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, India.*

### **Authors' contributions**

*This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.*

### **Article Information**

DOI: 10.9734/JPRI/2021/v33i64B35741

### **Open Peer Review History:**

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/77928>

**Original Research Article**

**Received 25 October 2021**  
**Accepted 28 December 2021**  
**Published 30 December 2021**

### **ABSTRACT**

**Background:** Recently, nanoparticles have been playing a pivotal role in modern material development. Nanotechnology has provided great possibilities in various fields of science and technology. The antioxidant characteristics of *Aspalathus linearis*, also known as rooibos, include antimutagenic, anticarcinogenic, anti-inflammatory, and antiviral capabilities.

**Aim:** To determine the anti-inflammatory and antioxidant activity of copper nanoparticles synthesized using red tea.

**Materials and Methods:** Preparation of the red tea extract, synthesis of copper nanoparticles, preparation of nanoparticles powder and then antioxidant and anti-inflammatory activity of nanoparticles were analysed. Antioxidant activity and anti-inflammatory activity was assessed using DPPH (2,2-diphenyl-1-picryl-hydrazyl-hydrate) assay and inhibition of albumin denaturation assay. The standard used was diclofenac sodium in various concentrations.

**Results:** The formation of copper nanoparticles was indicated by the peak found in the spectroscopy. Copper nanoparticles synthesized using red tea showed highest absorbance at a

<sup>≡</sup> Senior Lecturer,

<sup>∞</sup> Associate Professor,

\*Corresponding author: E-mail: [arvinar.sdc@saveetha.com](mailto:arvinar.sdc@saveetha.com);

concentration of 50 $\mu$ l (82%) when it was subjected to DPPH assay to check for its antioxidant property at a wavelength of about 517 nm. Copper nanoparticles synthesized using red tea showed highest absorbance at a concentration of 50 $\mu$ l (92.2%) when it was subjected to inhibition of albumin denaturation assay to analyse for its anti-inflammatory activity at a wavelength of about 660 nm.

**Conclusion:** The present study suggests that red tea mediated copper nanoparticles showed good antioxidant activity and anti-inflammatory activity. It can be concluded that the antioxidant activity of red tea is not as efficient as Diclofenac but it can be more efficient when it's concentration is raised to safe levels and anti-inflammatory activity of red tea is as efficient as Diclofenac.

**Keywords:** Copper nanoparticles; red tea; antioxidant; anti-inflammatory; green synthesis; innovative.

## 1. INTRODUCTION

Nanotechnology, often known as nanoscience, is the study of an applied science at the atomic or molecular level. Nanoscience and nanotechnology have seen tremendous progress in research and applications in recent years. Nanotechnology's application in medicine, specifically drug delivery, is expected to grow substantially [1]. Nanoparticles in pharmaceutical research are used to reduce drug toxicity and adverse effects. The fact that these nanoparticles have a surface to mass ratio that is significantly higher than that of other particles, as well as their quantum characteristics and capacity to absorb and convey other substances, makes them appealing for medicinal applications [2].

Nanoparticles have a huge (functional) surface that can bind, adsorb, and transport other substances like medicines, probes, and proteins. Copper, as well as Au, Ag, Pd, and Pt compounds, are commonly employed these days. Copper is a good conductor of electricity [3,4]. Because of the low costs. This metal is extremely important in current electronic circuits. Copper nanoparticles have attracted the attention of scientists for their superior catalytic behaviour, conductivity of electricity, and surface enhanced Raman scattering activity and better compatibility, and are expected to be used in future nano devices as crucial components [5,6]. Nanowires made of copper can be used to make magnetic devices, nanosensors, electron emitters, and other electrical devices and are employed in nanoelectronics [7].

The focus of nanotechnology research has switched significantly from traditional applications to green processes in recent years [8-14]. For the synthesis of nan-oparticles, this method can use natural plant extracts, essential oils, fungus, or bacteria. Green synthesis aims to reduce the use and production of harmful compounds like

formaldehyde and sodium borohydride, which are often employed as reducing agents in traditional procedures [15]. Plant extracts are also employed as effective stabilising agents of nanoparticle suspension in environmentally friendly methods, which eliminates the usage of additional chemical compounds during nanoparticle synthesis [16]. Our team has extensive knowledge and research experience that has translated into high quality publications [17-36]. The aim of this study was to determine the anti-inflammatory and antioxidant activity of copper nanoparticles synthesized using red tea.

## 2. MATERIALS AND METHODS

### 2.1 Preparation of the Extract

In a beaker 1g of red tea was added to 100ml of distilled water and mixed well. And then boiled for 15 minutes at 70-80°C. The solution was filtered by using Whatman no. 1 filter paper and funnel. The filtered extract was collected and stored for further use (Fig. 1, Fig. 2).



**Fig. 1. Mixture of red tea in distilled water**

### 2.2 Synthesis of ZnO Nanoparticles

20mM of CuSO<sub>4</sub> was prepared using distilled water. The red tea extract was then added, and

distilled water was used to make a 100ml solution. Then, using a magnetic stirrer in an orbital shaker, thoroughly mix everything together. To validate the presence of copper nanoparticles produced, the absorbance was measured using a UV - Visible Spectrometer at regular intervals. Every two hours, a reading was taken to observe the colour change. To collect the nanoparticles, the final reaction mixture was centrifuged for 10 minutes. The finished reaction mixture was centrifuged for 10 minutes at 800 rpm in a Lark refrigerated centrifuge. After that, the samples were collected and stored in an airtight Eppendorf tube (Fig. 3, Fig. 4).




Fig. 2. Concentrated extract of red tea




Fig. 3. Mixture of CuSO<sub>4</sub> and red tea extract

### 2.3 Antioxidant Activity of Copper Nanoparticles Synthesized Using Red Tea

A test tube rack was arranged with five test tubes, each marked with a label signifying the

various concentrations of the extract from 10 to 50  $\mu$ l. Each test tube was loaded with DPPH (2,2-diphenyl-1-picryl-hydrazyl-hydrate), ethanol and the extract. The DPPH free radical method produces a violet solution in ethanol and is an antioxidant assay based on electron transfer. In the presence of an antioxidant molecule, this free radical, which is stable at room temperature, was diminished, resulting in a colourless ethanol solution. A UV spectrophotometer was used to determine the rate of its activity.




Fig. 4. The final reaction solution with red tea mediated copper nanoparticles

### 2.4 Anti Inflammatory Activity of Copper Nanoparticles Synthesized Using Red Tea (INHIBITION of Albumin Denaturation Assay)

The reagent for the assay was BSA (Bovine serum albumin). BSA (bovine serum albumin) accounts for over 60% of all proteins in animal serum. It's often employed in cell culture, especially when protein supplementation was required but the other serum components were undesirable. When BSA was heated, it denatures and begins to express antigens. 5 test tubes containing varied concentrations (10-50  $\mu$ l) of red tea extract were mixed with 2ml of 1 percent Bovine albumin fraction, and the pH of the reaction mixture was adjusted to 6.8 using 1N HCL. In a water bath, the reaction mixture was incubated at room temperature for 20 minutes. The mixture was allowed to cool to room temperature before measuring the absorbance at 660 nm. The standard used was diclofenac sodium in various concentrations.

Formula used for calculating the % Inhibition:

$$\% \text{ Inhibition} = \frac{\text{Control O.D} - \text{Sample O.D}}{\text{Control O.D}}$$

### 3. RESULTS

#### 3.1 Antioxidant Activity of Copper Nanoparticles Synthesized Using Red Tea

UV-Vis Spectroscopy was used to confirm the absorbance of free radicals by the extract subjected to the DPPH assay to analyze its antioxidant activity. The UV – Vis Spectra was recorded for the prepared copper nanoparticles synthesized using red tea. From the spectra, it was observed that the extract at 517 nm had the highest absorbance at a concentration of 50  $\mu\text{l}$  (82%), indicating significant antioxidant properties, as potent as DPPH itself. This confirms the potent efficacious antioxidant activity of the red tea extract (Fig. 5, Fig. 6).

#### 3.2 Anti Inflammatory Activity of Copper Nanoparticles Synthesized Using Red Tea


UV-Vis spectroscopy is used to confirm the absorbance of free radicals by the extract subjected to the inhibition of albumin denaturation assay to analyze its anti-inflammatory activity. [31] The UV – Vis Spectra

was recorded for the prepared copper nanoparticles using red tea extract. It was observed from the spectra that the extract at 660 nm had the highest absorbance at a concentration of 50 $\mu\text{l}$  (92.2%), which was indicative for significant anti-inflammatory activity, as potent as diclofenac sodium itself. This confirms the potent efficacious anti-inflammatory activity of the copper nanoparticles synthesized using red tea extract (Fig. 7, Fig. 8).


### 4. DISCUSSION

This study was done to analyse the anti-inflammatory and antioxidant activity of copper nanoparticles synthesized using red tea.


In the present study, when subjected to DPPH assay it was found that red tea mediated copper nanoparticles showed highest absorbance at a concentration of 50 $\mu\text{l}$  (82%) to check for its antioxidant property at a wavelength of about 517 nm. When subjected to inhibition of albumin denaturation assay, copper nanoparticles synthesized using red tea showed highest absorbance at a concentration of 50 $\mu\text{l}$  (92.2%) to check for its anti-inflammatory activity at a wavelength of about 660 nm.




**Fig. 5.** The bar graph shows the comparison of the mean absorbance of antioxidant activity of both standard and red tea extract at various concentrations. The X axis represents the various concentrations of standard and red tea extract in units of  $\mu\text{L}$  and the Y axis represents the mean absorbance. Blue represents the standard and green represents red tea. The graph shows that the mean absorbance of red tea was significantly lesser when compared to the standard at all the concentrations even though the magnitude of difference was lesser at higher concentrations ( $p < 0.05$ ) (unpaired t test)



**Fig. 6.** The figure shows the mean absorbance of antioxidant properties of red tea extract at different concentrations. The X axis represents the various concentrations of red tea extract in units of µL and the Y axis represents the mean absorbance. There was a significant increase in the mean absorbance from lower concentration to higher concentrations. ( $p < 0.05$ ) (One Way ANOVA followed by Tukey’s post hoc analysis)



**Fig. 7.** The bar graph shows the comparison of the mean absorbance of anti-inflammatory activity of both standard and red tea extract at various concentrations. The X axis represents the various concentrations of standard and red tea extract in units of µL and the Y axis represents the mean absorbance. Blue represents the standard and green represents red tea. The graph shows that the mean absorbance of red tea was significantly higher when compared to the standard at all the concentrations ( $p < 0.05$ ) (unpaired t test)



**Fig. 8.** The figure shows the mean absorbance of anti-inflammatory properties of red tea at different concentrations. The X axis represents the various concentrations of red tea extract in units of  $\mu\text{L}$  and the Y axis represents the mean absorbance. There was a significant increase in the mean absorbance from lower concentration to higher concentrations. ( $p < 0.05$ ) (One Way ANOVA followed by Tukey's post hoc test analysis)

The antioxidant activity of zinc oxide nanoparticles generated using grape seed extract was examined by Akshaya K et al, who discovered that the extract at 517 nm exhibited the maximum radical scavenging activity at a concentration of 25 L, indicating considerable antioxidant activity [37]. Another study on the anti-inflammatory activity of titanium dioxide nanoparticles synthesised with grape seed extract found that the titanium dioxide nanoparticles synthesised with grape seed extract have good anti-inflammatory activity and could be used as pastes, gels, and other topical applications in the future [38]. Another study looked at the anti-inflammatory activity of selenium nanoparticles made with clove and cinnamon. It found that the selenium nanoparticles made with clove and cinnamon have good anti-inflammatory action, which helps to reduce the negative effects [39]. Another investigation on the antibacterial and antioxidant activities of clove and cinnamon herbal formulations discovered that the clove and cinnamon extract has antimicrobial and antioxidant potential [40].

Suresh M et al. investigated the antioxidant activity of a *Syzygium aromaticum* and *Cinnamomum verum* formulation mediated by silver nanoparticles and discovered that the formulation has an antioxidant impact that rises

with concentration [41]. The antioxidant activity of grape seed mediated  $\text{TiO}_2$  nanoparticles was investigated in another work, which revealed efficient and powerful antioxidant activities of grape seed mediated  $\text{TiO}_2$  nanoparticles [42].

The anti-inflammatory and cytotoxic effects of a clove and cinnamon herbal formulation were studied by Pranati T et al, who discovered that the produced clove and cinnamon extract was a powerful antioxidant and antibacterial agent [13]. A prior investigation on the antioxidant activity of clove and cinnamon herbal formulations revealed that clove and cinnamon have the potential to be efficient antioxidants [43]. Devi BV et al investigated the anti-inflammatory efficacy of zinc oxide nanoparticles generated using grape seed extract and discovered that the zinc oxide nanoparticles made with grape seed extract are a strong anti-inflammatory drug with few adverse effects [44]. The antibacterial, antioxidant, and cytotoxic effects of an aqua alcoholic extract of grape seed were studied by Kandhan TS et al., who discovered the extract's significant antioxidant and antimicrobial activities [45].

Similar to these studies, we have assessed the antioxidant and anti-inflammatory activity of copper nanoparticles synthesized using red tea. Antioxidants have the ability to attach to free radicals before they do harm. Because some

antioxidants have a phenolic ring in their chemical structure, they are referred to as polyphenols. Rooibos tea includes polyphenol antioxidants, such as flavonoids and phenolic acids, which are powerful free radical scavengers, according to laboratory studies [46]. According to Bramati L et al, Unfermented rooibos had a total antioxidant activity that was 2-fold higher than fermented rooibos. As a result, red tea possesses antioxidant properties [47]. Red tea's antioxidant action may help to reduce DNA damage and inflammation. Therefore showing that red tea has anti-inflammatory activity with abundant flavonoids [48]. From the above studies mentioned, red tea has antioxidant activity but there are no studies which incorporated red tea in nanoparticles. So, we have analysed the antioxidant and anti-inflammatory activity of red tea. Even though we have found out that red tea nanoparticles have antioxidant and anti-inflammatory activity, these findings need to be confirmed with more clinical trials for clinical application.

## 5. CONCLUSION

The present study suggests that red tea mediated copper nanoparticles showed good antioxidant activity and anti-inflammatory activity [49-62]. It can be concluded that the antioxidant activity of red tea is not as efficient as Diclofenac but it can be more efficient when its concentration is raised to safe levels and anti-inflammatory activity of red tea is as efficient as Diclofenac.

## DISCLAIMER

The products used for this research are commonly and predominantly use products in our area of research and country. There is absolutely no conflict of interest between the authors and producers of the products because we do not intend to use these products as an avenue for any litigation but for the advancement of knowledge. Also, the research was not funded by the producing company rather it was funded by personal efforts of the authors.

## CONSENT

It is not applicable.

## ETHICAL APPROVAL

It is not applicable.

## ACKNOWLEDGMENT

The authors would like to acknowledge the help and support rendered by the Department of Periodontics, Blue Lab, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University for their constant assistance with the research.

## COMPETING INTERESTS

Authors have declared that no competing interests exist.

## REFERENCES

1. Thomas S, Kalarikkal N, Manuel Stephan A, Raneesh B. *Advanced Nanomaterials: Synthesis, Properties and Applications*. CRC Press. 2014;402.
2. Mohapatra S, Leelavathi L, Rajeshkumar S,D. SS, P. J. Assessment of Cytotoxicity, Anti-Inflammatory and Antioxidant Activity of Zinc Oxide Nanoparticles Synthesized Using Clove and Cinnamon Formulation - An In-Vitro Study [Internet]. *Journal of Evolution of Medical and Dental Sciences*. 2020;9:1859–64. Available:<http://dx.doi.org/10.14260/jemds/2020/405>
3. Pelton JT, McLean LR. Spectroscopic methods for analysis of protein secondary structure. *Anal Biochem*. 2000;277(2):167–76.
4. Chapple ILC, Hamburger J. *Periodontal Medicine - A Window on the Body*. Quintessenz Verlag. 2019;250.
5. Nirmala JG, Grace Nirmala J, Evangeline Celsia S, Swaminathan A, Narendhirakannan RT, Chatterjee S. Cytotoxicity and apoptotic cell death induced by *Vitis vinifera* peel and seed extracts in A431 skin cancer cells [Internet]. *Cytotechnology*. 2018;70:537–54. Available:<http://dx.doi.org/10.1007/s10616-017-0125-0>
6. Shukla AK, Iravani S. *Green Synthesis, Characterization and Applications of Nanoparticles*. Elsevier. 2018;548.
7. Wu S, Rajeshkumar S, Madasamy M, Mahendran V. Green synthesis of copper nanoparticles using *Cissus vitifera* and its antioxidant and antibacterial activity against urinary tract infection pathogens

- [Internet]. Artificial Cells, Nanomedicine, and Biotechnology. 2020; 48:1153–8. Available:<http://dx.doi.org/10.1080/21691401.2020.1817053>
8. Sagana M, Rajasekar A, Rajeshkumar S. Antifungal activity of grape seed extract mediated zinc oxide nanoparticles - an invitro study. *Plant cell biotechnology and molecular biology*. 2020;21(29-30):14–20.
  9. Yuvashree CS, Rajasekar, Rajeshkumar S. Cytotoxic effect of titanium dioxide nanoparticles synthesized using grape seed extract: An in vitro study. *Plant cell biotechnology and molecular biology*. 2020;21(31-32):120–6.
  10. Shivani N, Rajasekar A, Rajeshkumar S. Antifungal activity of grape seed extract mediated titanium oxide nanoparticles against candida albicans: an in vitro study. *Plant cell Biotechnology and Molecular biology*. 2020;21(35-36):8–15.
  11. Devi BV, Rajasekar A, Rajeshkumar S. Antiinflammatory activity of zinc oxide nanoparticles synthesised using grape seed extract: an in vitro study. *Plant cell biotechnology and molecular biology*. 2020;21(33-34):6–16.
  12. Pereira WD, Rajasekar A, Rajeshkumar S. Green synthesis of selenium nanoparticles (senps) using aqueous extract of clove and cinnamon. *Plant cell biotechnology and molecular biology*. 2020;21(29-30):85–91.
  13. Pranati, Rajasekar A, Rajeshkumar S. Anti inflammatory and cytotoxic effect of clove and cinnamon herbal formulation. *Plant cell Biotechnology and Molecular Biology*. 2020;21(29-30):69–77.
  14. Anjum AS, Rajasekar, Rajeshkumar S. Synthesis and characterization of grape seed mediated titanium dioxide nanoparticles: An *In Vitro* study. *Plant cell biotechnology and molecular biology*. 2020;21(33-34):17–23.
  15. Koch CC. *Nanostructured Materials: Processing, Properties, and Applications*. William Andrew Pub. 2007;760.
  16. Jain S, Mehata MS. Medicinal Plant Leaf Extract and Pure Flavonoid Mediated Green Synthesis of Silver Nanoparticles and their Enhanced Antibacterial Property. *Sci Rep*. 2017;7(1):15867.
  17. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. *J Periodontol*. 2012;89(10):1241–8.
  18. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. *Hypertens Res*. 2020;43(7):729–30.
  19. Faleh AA, Sukumaran A, NS. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. *Int J Biol Macromol*. 2018;120(Pt A):876–85.
  20. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. *Cochrane Database Syst Rev*. 2018;11:CD011423.
  21. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. *Hypertens Res*. 2020;43(8):851–3.
  22. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. *Cell Mol Immunol*. 2019;16(12):935–6.
  23. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm. *Comput Commun*. 2019;148:176–84.
  24. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). *J Med Syst*. 2018;42(10):183.
  25. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. *J Dent Educ*. 2019;83(4):445–50.
  26. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating. *Molecules* [Internet]. 2018;23(6). Available:<http://dx.doi.org/10.3390/molecules23061429>
  27. Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human



- Mesenchymal Stem Cells. *Biomolecules* [Internet]. 2018;8(3). Available:<http://dx.doi.org/10.3390/biom8030068>
28. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from Cuttlefish Bone: Isolation, Characterizations, and Applications. *Biotechnol Bioprocess Eng.* 2018 Aug 1;23(4):383–93.
  29. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network. *Measurement.* 2019;135:672–7.
  30. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod.* 2021;47(8):1198–214.
  31. Ramani RH, Tilakaratne P, Sukumaran WM, Ramasubramanian G, Krishnan A, RP. Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris-A review. *Oral Dis* [Internet]; 2021. Available:<http://dx.doi.org/10.1111/odi.13937>
  32. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis* [Internet]; 2021. Available:<http://dx.doi.org/10.1111/odi.13798>
  33. Sarode SC, Gondivkar S, Sarode GS, Gadball A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol.* 2021;105390.
  34. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol.* 2021;105375.
  35. Vellappally S, Abdullah Al-Kheraif A, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network. *J Ambient Intell Humaniz Comput* [Internet]; 2018. Available:<https://doi.org/10.1007/s12652-018-1166-8>
  36. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. *Risk Manag Healthc Policy.* 2021;14:2851–61.
  37. Akshaya K, Rajasekar A, Rajeshkumar S. Antioxidant activity of zinc oxide nanoparticles synthesised using grape seed extract: An *In vitro* study. *Plant cell biotechnology and molecular biology.* 2020;21–9.
  38. Website [Internet]. Available:<https://www.ikprress.org/index.php/PCBMB/article/view/5290>
  39. Dharahaas C, Rajasekar A, Rajeshkumar S. Anti inflammatory activity of selenium nanoparticles synthesised using clove and cinnamon: An *In vitro* study. *Plant cell biotechnology and molecular biology.* 2020;144–51.
  40. Jagadish Rajkumaar R, Rajasekar A, Rajeshkumar S. Antimicrobial and antioxidant activity of clove and cinnamon herbal formulation: an in vitro study. *Plant cell biotechnology and molecular biology.* 2020;11–7.
  41. Suresh M, Rajasekar A, Rajeshkumar S. Antioxidant activity of syzygium aromaticum and cinnamomum verum formulation mediated silver nano particles. *Plant Cell Biotechnology and Molecular biology.* 2020;50–7.
  42. Neha Sharma M, Rajasekar A, Rajeshkumar S. Antioxidant activity of grape seed mediated tio2 nanoparticles: an in vitro study. *Plant Cell Biotechnology and Molecular Biology.* 2020;24–31.
  43. Pillay SR, Rajasekar A, Rajeshkumar S. Preparation of selenium nanoparticles using herbal formulation and its antioxidant activity: An *In Vitro* study. *Plant cell biotechnology and molecular biology.* 2020;49–56.
  44. Vaishnavi Devi B, Rajasekar A, Rajeshkumar S. Antiinflammatory activity of zinc oxide nanoparticles synthesised using grape seed extract: an in vitro study. *Plant cell biotechnology and molecular biology.* 2020;6–16.
  45. Kandhan TS, Rajasekar A, Rajeshkumar S. Grape seed aqua alcoholic extract preparation and its antioxidant, antimicrobial and cytotoxic effect - an in vitro study. *Plant Cell Biotechnology and molecular biology.* 2020;18–26.

46. Meghwal M, Goyal MR. Developing Technologies in Food Science: Status, Applications, and Challenges. CRC Press; 2017;356.
47. Bramati L, Aquilano F, Pietta P. Unfermented rooibos tea: quantitative characterization of flavonoids by HPLC-UV and determination of the total antioxidant activity. *J Agric Food Chem.* 2003;51(25): 7472–4.
48. Baba H, Ohtsuka Y, Haruna H, Lee T, Nagata S, Maeda M, et al. Studies of anti-inflammatory effects of Rooibos tea in rats. *Pediatr Int.* 2009;51(5):700–4.
49. Danda AK. Comparison of a single noncompression miniplate versus 2 noncompression miniplates in the treatment of mandibular angle fractures: a prospective, randomized clinical trial. *J Oral Maxillofac Surg.* 2010;68(7):1565–7.
50. Robert R, Justin Raj C, Krishnan S, Jerome Das S. Growth, theoretical and optical studies on potassium dihydrogen phosphate (KDP) single crystals by modified Sankaranarayanan–Ramasamy (mSR) method [Internet]. *Physica B: Condensed Matter.* 2010;405:20–4. Available:<http://dx.doi.org/10.1016/j.physb.2009.08.015>
51. Krishnan V, Lakshmi T. Bioglass: A novel biocompatible innovation. *J Adv Pharm Technol Res.* 2013;4(2):78–83.
52. Soh CL, Narayanan V. Quality of life assessment in patients with dentofacial deformity undergoing orthognathic surgery—A systematic review [Internet]. *International Journal of Oral and Maxillofacial Surgery.* 2013;42:974–80. Available:<http://dx.doi.org/10.1016/j.ijom.2013.03.023>
53. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Schiff base complexes of rare earth metal ions: Synthesis, characterization and catalytic activity for the oxidation of aniline and substituted anilines [Internet]. *Journal of Organometallic Chemistry.* 2014;753:72–80. Available:<http://dx.doi.org/10.1016/j.jorganchem.2013.12.014>
54. Dhinesh B, Isaac Joshua Ramesh Lalvani J, Parthasarathy M, Annamalai K. An assessment on performance, emission and combustion characteristics of single cylinder diesel engine powered by Cymbopogon flexuosus biofuel [Internet]. *Energy Conversion and Management.* 2016;117:466–74. Available:<http://dx.doi.org/10.1016/j.enconman.2016.03.049>
55. PradeepKumar AR, Shemesh H, Jothilatha S, Vijayabharathi R, Jayalakshmi S, Kishen A. Diagnosis of Vertical Root Fractures in Restored Endodontically Treated Teeth: A Time-dependent Retrospective Cohort Study. *J Endod.* 2016;42(8):1175–80.
56. Vijayakumar GNS, Nixon Samuel Vijayakumar G, Devashankar S, Rathnakumari M, Sureshkumar P. Synthesis of electrospun ZnO/CuO nanocomposite fibers and their dielectric and non-linear optic studies [Internet]. *Journal of Alloys and Compounds.* 2010;507:225–9. Available:<http://dx.doi.org/10.1016/j.jallcom.2010.07.161>
57. Kavitha M, Subramanian R, Narayanan R, Udhayabanu V. Solution combustion synthesis and characterization of strontium substituted hydroxyapatite nanocrystals [Internet]. *Powder Technology.* 2014;253:129–37. Available:<http://dx.doi.org/10.1016/j.powtec.2013.10.045>
58. Sahu D, Kannan GM, Vijayaraghavan R. Size-Dependent Effect of Zinc Oxide on Toxicity and Inflammatory Potential of Human Monocytes [Internet]. *Journal of Toxicology and Environmental Health, Part A.* 2014;77:177–91. Available:<http://dx.doi.org/10.1080/15287394.2013.853224>
59. Neelakantan P, Cheng CQ, Mohanraj R, Sriraman P, Subbarao C, Sharma S. Antibiofilm activity of three irrigation protocols activated by ultrasonic, diode laser or Er:YAG laser in vitro [Internet]. *International Endodontic Journal.* 2015;48:602–10. Available:<http://dx.doi.org/10.1111/iej.12354>
60. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Synthesis, spectroscopic characterization and antibacterial studies of lanthanide(III) Schiff base complexes containing N, O donor atoms [Internet]. *Vols. 1056-1057, Journal of Molecular Structure.* 2014;307–13. Available:<http://dx.doi.org/10.1016/j.molstruc.2013.10.014>

61. Gopalakannan S, Senthilvelan T, Ranganathan S. Modeling and Optimization of EDM Process Parameters on Machining of Al 7075-B4C MMC Using RSM [Internet]. Procedia Engineering. 2012;38:685–90. Available:<http://dx.doi.org/10.1016/j.proeng.2012.06.086>
62. Parthasarathy M, Isaac JoshuaRamesh Lalvani J, Dhinesh B, Annamalai K. Effect of hydrogen on ethanol-biodiesel blend on performance and emission characteristics of a direct injection diesel engine. Ecotoxicol Environ Saf. 2016;134(Pt 2):433–9.

---

© 2021 Bharathi et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

*Peer-review history:*

*The peer review history for this paper can be accessed here:*  
<https://www.sdiarticle5.com/review-history/77928>